






QUALITY PLUS
HIGH PERFORMANCE



QUA
HIGH

MS LACQUER

Caslek MS Lacquer is an acrylic Lacquer with medium solids content offering a flawless mirror-like finish. It is easy to apply, fast drying, and has an excellent gloss level.

TECHNICAL INFORMATION									
    	Substrates	Caslek MS Lacquer can be applied over solvent-based basecoat and properly prepared paint work in good conditions.							
	Mixing ratio	<table border="1"><tr><td>MS Lacquer</td><td>:</td><td>Hardener</td></tr><tr><td>2</td><td>:</td><td>1</td></tr></table>		MS Lacquer	:	Hardener	2	:	1
	MS Lacquer	:	Hardener						
	2	:	1						
	Pot life	With hardener, 3 hours at 23°C							
Spray gun tips	Spray gun: 1.3 mm Conventional: 3.0-3.5 bar/45-50 psi inlet HVLP: 2 bar/26-30 psi inlet								
Spray method	Application Viscosity: 16-18 seconds – DIN Cup 4 at 23°C Coats & Thickness: 2-3 coats, total 40-60um Flash-Off Time: At 23°C, 5-10 minutes between coats								

N
1.
2.
3.
4.